



LABORATORY GROWN DIAMOND IDENTIFICATION REPORT



LG414073334
ANTWERP, March 9, 2020

LABORATORY GROWN
DIAMOND
OVAL BRILLIANT
WEIGHT 0.31 CARAT
COLOR D
CLARITY VS 2
POL-SYM VERY GOOD
PROP EXCELLENT
FLUO NONE

NUMBER LG414073334 ANTWERP, March 9, 2020

DESCRIPTION LABORATORY GROWN DIAMOND

SHAPE AND CUT OVAL BRILLIANT

CARAT WEIGHT 0.31 CARAT

Measurements 5.48 x 3.86 x 2.31 mm

CLARITY GRADE VS 2

COLOR GRADE D

Fluorescence NONE

FINISH

Polish - Symmetry VERY GOOD

Proportions EXCELLENT

Table Size 59.5%

Crown Height 12.5%

Pavilion Depth 43.5%

Girdle Thickness MEDIUM TO SLIGHTLY THICK (FACETED)

Culet POINTED

Total Depth 59.8%

COMMENT This Laboratory Grown Diamond was created by High Pressure High Temperature (HPHT) growth process. Type II

LASERSCRIBE LABGROWN IGI LG414073334

IDENTIFICATION FEATURES

Crystal, Feather

CLARITY SCALE


FLAWLESS/ INTERNALLY FLAWLESS	VERY VERY SLIGHTLY INCLUDED		VERY SLIGHTLY INCLUDED		SLIGHTLY INCLUDED		INCLUDED		
	VVS ₁	VVS ₂	VS ₁	VS ₂	SI ₁	SI ₂	I ₁	I ₂	I ₃

COLOR SCALE

COLORLESS			NEAR COLORLESS			SLIGHTLY TINTED			VERY LIGHT			LIGHT					FANCY COLOR					
D	E	F	G	H	I	J	K	L	M	N	O	P	Q	R	S	T		U	V	W	X	Y

The laboratory grown diamond described in this report has been graded, tested, analyzed, examined and/or inscribed by International Gemological Institute (IGI). Laboratory grown diamonds are diamond crystals created by scientific means and representing essentially all physical, chemical and optical characteristics of natural diamonds. IGI employs and utilizes those techniques and equipment currently available to IGI including without limitations: DiamondView, DiamondSure, FTIR spectroscopy, UV VIS NIR absorption spectrometer, EDXRF spectroscopy, PL (RAMAN) spectrometers.

5.48 x 3.86 x 2.31 mm



Note: Profile not to actual proportions

0-m Security features included in this document are hologram, watermarked paper and additional features not listed, that, as a composite, exceed industry security standards.



See terms and conditions on reverse

All rights reserved. No part of this report may be reproduced or transmitted in any form or by any means, without permission in writing from International Gemological Institute